

WAXES

WR Waxes

PRODUCT CODE	ASTM Color (ASTM D 1500)		Saybolt Color (ASTM D 156)		Congealing Point, °C (ASTM D 938)		Oil Content, % (wt) (ASTM D 721)		Needle Penetration at 25°C, dmm (ASTM D 1321)		Kinematic Viscosity at 100°C, cSt (ASTM D445)	
	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max
WR 51*	-	-	+28	+30	50	52	-	0,5	15	20	Typical 3,5	
WR 53*	-	-	+28	+30	52	54	-	0,5	15	20	Typical 3,5	
WR 55*	-	-	+28	+30	54	56	-	0,5	15	20	Typical 3,5	
WR 57*	-	-	+28	+30	56	58	-	0,5	14	18	Typical 3,5	
WR 58*	-	-	+25	+30	58	60	-	0,5	14	20	Typical 4,0	
WR 59	-	-	+25	+30	58	60	-	1,0	14	20	Typical 4,5	
WR 44	-	-	+24	+30	62	66	-	3,0	15	25	5,0	7,0
WR 45	-	-	+10	+15	58	64	-	3,5	15	30	4,0	6,0
WR 47*	-	-	+25	+30	62	66	-	1,5	15	25	4,5	6,5
WR 48	-	0,5	-	-	52	60	2,0	6,0	30	50	3,0	5,0
WR 60	-	-	+5	+10	59	66	-	5,0	-	55	5,0	7,0
WR 63	-	-	+2	+10	57	65	-	10,0	-	65	5,0	7,0
WR 65	-	-	+2	+10	58	64	-	14,0	-	65	5,5	7,0
WR 66	-	1,0	-	-	58	64	-	15,0	-	65	5,5	7,0
WR 67	-	1,5	-	-	-	68	-	20,0	Typical 70		Typical 8,0	
WR 69	-	1,5	-	-	-	68	-	25,0	Typical 80		Typical 10,0	
WR 71	-	2,0	-	-	68	75	-	3,0	15	40	9,0	15,0
WR 72*	-	1,5	-	-	68	75	-	2,0	15	35	9,0	15,0
WR 73*	-	1,5	-	-	70	76	-	2,0	22	28	9,0	15,0
WR 75*	-	-	+20	-	70	76	-	2,0	-	28	Typical 15,3	

Due to continual product research and development, the information contained herein is subject to change without notification

These products are, on request, in compliance with FDA Regulations covered under Title 21 § 172.886